

**RECEIVED**  
**CENTRAL FAX CENTER**  
**SEP 12 2006**

Application No. 10/512,036  
Art Unit 1762  
AMENDMENT  
Page 3

### **ABSTRACT AMENDMENTS**

Please replace the abstract filed originally with the following abstract:

For treating resin coated decorative papers, a solution of sodium aluminate in deionized water is applied, during printing with metal effect inks by gravure printing by a fond or subcoat cylinder. The solution has a pH-value between pH 9 and pH 14.